



**General Product Information:**

Cellular Glass insulation is manufactured by melting glass powder, adding a foaming agent and creating a bun of insulation. This material can then be cut and shaped into various insulating products. It is comprised of 100% glass (no binders or filler) with individual sealed glass cells. This creates a product with excellent thermal and floatation properties. Since the material is closed cell insulation, it has zero moisture permeability. The glass composition also makes it resistant to cold and heat, providing a wide temperature service range. The product does not age and produces consistent insulation values. Because the material will not “wick” any fluid, it is preferable to use when flammable chemicals are present. High compressive strength, and dimensionally stable.

---

**Description & Common Applications:**

The insulation is commonly used within industrial facilities, offshore platforms and cold storage. Other applications include Chilled Water Pipes and Equipment, Stainless Steel Hot Water lines, Hot Oil Piping & Equipment, LNG Piping, Green Roof Insulation, Underground Steam, Cold process Pipe and Equipment, Tanks, Ethylene Piping and Equipment, Fireproof Building Panels.



## Technical Data Sheet Cellular Glass Insulation

**Compliance and Performance:** ASTM C 552 Standard Specification for Cellular Glass Thermal Insulation

**Average Density:** 120kg/m<sup>3</sup>, 7.5lb/ft<sup>3</sup>, ASTM C303-2010

**Compressive Strength:** Average – 700 kpa, 101 psi, ASTM C165–2012

**Flexural Strength:** Average – 606 kpa, 88 psi, EN 12089

**Service Temperature:** -268°C / 480°C, -450°F / 896°F

**Thermal Conductivity:** Average .043 W/(m K), 0.32 BTU in / (hr ft<sup>2</sup> F), ASTM C177 – 2013 @10°C

**Water Vapor Permeability:** 0.00 perm – in. ASTM E96 - 2000

**Moisture Resistance:** Moisture Sorption - 0.5% (Water % by Volume) ASTM C240

**Closed-Cell Content:** 97% ASTM D2856-1994, ISO 4590

**Corrosive Resistance:** Corrosiveness to Steel – Pass, Chloride Content - <25ppm, EN 13468

**Linear Expansion Coefficient:** Product does not shrink or swell, (-196 °C - 25°C), ASTM E228-2011

**Combustibility:** Non-Combustible – Will not burn, Flame Spread 0 – Smoke Developed 0, ASTM E136-2004

\*\*\*Please note, all testing has been completed in accordance to the above international standards\*\*\*

All data pertaining to the performance of the material, has been provided by the Manufacturer Zhejiang Dehe Insulation Technology

### Key Application Qualifiers:

- High Compressive Strength
- Non-combustible
- Closed Cell – 0 Perm
- Fire resistant
- Excellent thermal resistance
- Does not promote growth of fungi or mildew
- CFC and HCFC free product and process
- Made from natural and recycled materials



Multi-Glass Insulation Ltd. has no control over installation design and workmanship, accessory materials or application conditions. Multi-Glass Insulation Ltd. does not guarantee the performance or results of any installation containing these products. Multi-Glass Insulation Ltd.'s overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. The data sheet relates only to the specific material designed herein.

For more information: Multi-Glass Insulation Ltd. 610 Hanlan Road, Woodbridge Ontario L4L 4Y1  
Last revised: January 1<sup>st</sup> 2022